

## TEST REPORT


<b>Report Ref.</b>	LEI21110517A Original		
<b>Date Received</b>	05/11/2021	<b>Date Issued</b>	15/11/2021

<b>Company Name &amp; Address</b>	Camira Fabrics Limited Meltham Mills, MELTHAM , HD9 4AY
<b>Contact Name</b>	Rebecca Grimes

<b>Order Number</b>	83A14305
<b>Sample Description</b>	Oxygen
<b>Colour</b>	Inhale
<b>Quality</b>	Oxygen
<b>End Use</b>	Upholstery
<b>No Of Samples</b>	1
<b>Retailer</b>	General

Test	Method	Sample	Result
Martindale Abrasion Resistance	BS EN ISO 12947-2: 2016		See Results

Tests marked (^) in this report have been performed by an approved 3rd party laboratory.  
Tests marked (\*) in this report are not included in our UKAS scope of accreditation.



Heather Fletcher  
(Jobsheet Technician)

**Martindale Abrasion Resistance BS EN ISO 12947-2: 2016**

**Conditioning Parameters: 20°C±2°C & 65% rH±4% rH**

	Results	Requirement
Shade change @ 3000	4-5	
	Abrasion Resistance*	
Specimen 1	>100,000 Revs	
Specimen 2	>100,000 Revs	
Specimen 3	>100,000 Revs	
Overall result**	>100,000 Revs	
Test Information		
Test load:	12 kPa	
Fabric type	Woven	
Breakdown criteria	None found	
Inspection interval	Every 10,000 Revs	
Foam used	Yes	
Preparatory treatment	No	
*The abrasion resistance result is the last inspection point at which no breakdown was observed.		
**The overall result is the lowest individual test result of all the test specimens tested.		

Overall Test Result: See Results

Uncertainty: ±17.1%

Report Type	Issue Date	Revision Reason	Revision Description
Original	15-Nov-21	Complete Original Issue	N/A

*The client acknowledges and agrees that any services provided and/or reports produced by Intertek are done so within the limits of the scope of work agreed pursuant to the client's specific instructions. This report relates specifically to the sample(s) tested that were drawn and delivered by the client or their nominated third party. Intertek does not make any representation or warranty for any bulk samples or certify the bulk samples received from the client. Furthermore, Intertek does not provide a warranty or verification on the sample(s) representing any specific goods, material and/or shipment and only relate to the sample(s) as received and tested. Intertek have aimed to conduct the review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or willful misconduct. In no event, will the contents of any reports or any extracts, excerpts or parts of any reports be distributed or published without the prior written consent of Intertek in each instance. Only the client is authorized to permit copying or distribution of this report (and then only in its entirety). Any such third parties to whom this report may be circulated rely on the content of the report solely at their own risk.*

*The reported expanded uncertainty is based on a standard uncertainty multiplied by a coverage factor of  $k = 2$ , providing a level of confidence of approximately 95%. Unless otherwise specified all compliance and pass/fail statements are binary simple acceptance based on the tolerance interval and, with the exception of graded methods, a test uncertainty ratio greater (TUR) than 4:1. For graded methods the TUR will drop to as low as 0.5:1 when the tolerance limits are within a grade division of the upper scale limit. The Uncertainty budgets are stated for each Test method, these are for reference, and should be considered when results are on or close to Specification Limits / Requirements and in such cases it should be noted that the risk of false acceptance or rejection may be as high as 50%, for further information please refer to ILAC G8.*