



## TEST REPORT

**Client:** Camira Fabrics Ltd  
 Meltham Mills  
 Meltham  
 West Yorkshire  
 HD9 4AY

**Entry No:** 71973

**Date received:** 01/10/2015

**Client's Description:** Sample of fabric: Call 3718, Quality: INDIVIDUO LAGUNA, Run No: 266852

**Test Required:** Flammability BS 7176 Low Hazard

**Pre-treatment:** None

**Conditioning:** A minimum of 24 hours at 50+/-5% Relative Humidity, 23+/-2° C

**Date Tests Completed:** 02/10/2015

**Method of Test:** BS EN 1021-1: 2006 – smouldering cigarette  
 BS EN 1021-2: 2006 – match flame equivalent

Ignition Source	Observations	Result
Smouldering cigarette	No flaming or progressive smouldering was observed within one hour of placement of the cigarettes.	PASS
Match flame equivalent	Flaming ceased within the specified two minute period after removal of the butane flame and no progressive smouldering occurred.	PASS

**Note:** A 35 kg/m<sup>3</sup> CMHR foam (Carpenters RX36-125) which meets the requirements of Annex A of BS 7176 was used as the filling

The above tests relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

### Comments

BS 7176: 2007 + A1: 2011 relates to labelling of furniture. If an item of furniture was manufactured from a composite of the fabric and foam tested above then it would comply with the low hazard category flammability requirements provided that it was tested every 2.500 units or once per month as required by Para 5 of BS 7176.

-----End of Document-----

*This is hereby certified to be a correct return of the tests made of the items referred to herein*



Dale Brockbank  
 Materials Testing Manager  
 02 October 2015

- ❖ Unless instructed otherwise by the client sample remnants will be disposed of after 28 days.
  - ❖ Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
  - ❖ Uncertainty budgets for test methods contained within this report are available on request.
- This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.



1104