

## CERTIFICATE OF TESTING

For the Account Of: Camira Fabrics  
Meltham Mills, Meltham  
West Yorkshire HD9 4AY  
United Kingdom  
Contact: Rebecca Brook

Client's Identification: 24-7 Flax – Tanzanite Weft, Call 4285

**TEST PERFORMED** Abrasion Resistance of Textile Fabrics (Oscillatory Cylinder Method) ASTM D4157-13

**TEST RESULTS**

<b>Number of Double Rubs</b> 500,000	<b>Warp (Length) Specimens</b> No breakage / wear	<b>Fill (Width) Specimens</b> No breakage / wear
---	--	---

**INTERPRETATION USED**

- Option 1 The end point is reached on a woven fabric when two or more yarns have broken or on a knitted fabric, when a hole appears.
- Option 2 The end point is reached when there is a change in shade or appearance that is sufficient to cause a customer to complain.

**NOTES**

**Abradant Used:**  ACT Standard #10 Cotton Duck  Wire Screen  
**Samples Backed with Masking Tape:**  Yes  No  
**Tension:** 4 pounds  
**Compression:** 3 pounds

**ACCEPTANCE CRITERIA**


<b>A.C.T. Standard</b>	<b>Acceptance Criteria</b>
General Contract Upholstery	No appreciable breakage or wear after 15,000 double rubs
Heavy Duty Upholstery	No appreciable breakage or wear after 30,000 double rubs

**CONCLUSION**

Based on the above Results and the A.C.T. Standard, the item tested:

- Unrated
- General Contract Upholstery
- Heavy Duty Upholstery

**CERTIFICATION** I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

  
\_\_\_\_\_  
Authorized Signature