

(CALL 4863) Fusion NPBB10 – Wool rich moquette Fine sett, face to face with crinkle – FMVSS 302 - 5/09/2016

BV Report Ref: TR4094/180303

Submitted By: CAMIRA FABRICS LTD
MELTHAM MILLS, MELTHAM, WEST YORKSHIRE,
HD9 4AY – UNITED KINGDOM

Contact Name: REBECCA BROOK

Order Date: 25th August 2016

Order No: 6879

Date of Receipt: 30th August 2016



**BUREAU
VERITAS**

Bureau Veritas
Consumer
Products
Services UK Ltd
31 Kingsland
Grange
Woolston
Warrington
Cheshire
WA1 4RW

Item Description: Fusion NPBB10 - Wool rich moquette, Fine Sett, face to face with crinkle
Color: None Given
Style No: 298195 0103
End Use: Transport Seating
Claimed: Wool

Test Specification: FMVSS 302:1991 – Flammability of interior materials.

Test Details

Application time: 15 Seconds
Conditioning: 21 ± 5°C / 50% ± 10% RH, ≥24hrs
Gas used: Natural

Conclusion: The sample supplied **meets** the performance requirements of FMVSS 302:1991.

Authorized By: Mark Jones
Head of Flammability

Issue Date: 5th September 2016



Tests marked 'Not UKAS Accredited' in this report are not included in the UKAS schedule for this laboratory. Opinions and interpretations expressed herein are outside the scope of the UKAS Accreditation. The information contained within any report is based on current BVCPs UK Ltd knowledge and is given without guarantee. A satisfactory test report in no way implies that the product so tested is approved by BVCPs UK Ltd, UKAS or other body.

A report is a confidential document to the person or firm to whom it is issued and it will be strictly treated as such by BVCPs UK Ltd. It may not be reproduced either in its entirety or in part and may not be used for advertising. The person or firm to whom the report is issued may however show it or send it, or a certified copy thereof prepared by BVCPs UK Ltd, for the information of his customer, supplier or other persons directly concerned. BVCPs UK Ltd will not, without the written consent of the person or firm, enter into any discussion or correspondence with any third party concerning the contents of the report. In the event of the improper use of a report, BVCPs UK Ltd reserves the right to withdraw it or adopt any other remedy which may be appropriate. Samples submitted for testing are accepted on the understanding that the report issued shall not form the basis of or instrument for, any legal liability against BVCPs UK Ltd and applies specifically to the sample(s) tested and not necessarily to the bulk.

**Bureau Veritas Consumer Products Services UK Ltd, Registered in England & Wales, Company Number: 00852439
Registered Office: 31 Kingsland Grange, Woolston, Warrington, Cheshire, WA1 4RW**

(CALL 4863) Fusion NPBB10 – Wool rich moquette Fine sett, face to face with crinkle – FMVSS 302 - 5/09/2016

Report Reference: TR4094/180303

Item Description: Fusion NPBB10 - Wool rich moquette, Fine Sett, face to face with crinkle
Color: None Given
Style No: 298195 0103
End Use: Transport Seating
Claimed: Wool

Specimen Results: Flame applied to the pile surface of the fabric

Test Criteria	1	2	3	4
Direction of test	↑	↓	↑	↓
Thickness value of sample (Max/Min.) (mm)	2.94 2.65	2.72 2.63	3.29 2.60	2.91 2.80
Did specimen ignite?	NO	NO	NO	NO
Separation of flaming debris	NO	NO	NO	NO
Did specimen self-extinguished?	NO	NO	NO	NO
Burnt distance in (Inch)	0.0	0.0	0.0	0.0
Time in seconds to burnt distance	0.0	0.0	0.0	0.0
Burn rate inch/min	0.0	0.0	0.0	0.0

Pass/Fail Criteria:

Material shall not burn, nor transmit a flame front across its surface at a rate of more than 4 inches per minute. However, the requirement concerning transmission of a flame front shall not comply with a surface created by cutting of a test specimen for purpose testing.

If a material stops burning before it has burned for 1 minute from the start of timing, and has not burned more than 2 inches from the point where timing was started, it shall be considered to meet the burn rate requirement in the standard.