



DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

"We Test Per Your Request"

October 20, 2014

CAMIRA GROUP, INC.
2476 Waldorf Court N.W.
Grand Rapids, MI 49544

Reference: Laboratory Test Report
Lab Identification No. 12145
Invoice No. 43005 (Attached)

Dear Sir or Madam:

One (1) fabric sample, identified as **EBB**, was received and tested in accordance with the Classification Fire Test: BFD IX-1 issued by the Office of Fire Marshal of the Boston Fire Department (Revised 5/03). The results are as follows:

<u>Specimen Number</u>	<u>After Flame (sec)</u>		<u>After Glow (sec)</u>		<u>Char Length (in)</u>	
	<u>Length</u>	<u>Width</u>	<u>Length</u>	<u>Width</u>	<u>Length</u>	<u>Width</u>
1	0.0	0.0	0.0	0.0	3.8	4.4
2	0.0	0.0	0.0	0.0	4.1	4.5
3	0.0	0.0	0.0	0.0	3.5	3.8
Avg.					4.0	

The sample submitted meets the minimum requirements of the above standard. After flame shall not exceed two seconds. Flame propagation (char length) and after flame shall not extend beyond six inches from the bottom edge of the specimen. Propagating afterglow shall not exceed forty seconds; non-propagating afterglow in the charred area shall not exceed eighty seconds.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Bobby E. Puett

BEP/mr
Attachment