

Our Ref: SW/LS/BR

14 June 2018

Report 322531

Page 1 of 2

Camira Fabrics Limited
Meltham Mills
Meltham
West Yorkshire
HD9 4AY

Contact: Rebecca Grimes; Katy Longstaff

| | |
|-----------------------|--------------|
| DATE RECEIVED | : 8 JUN 2018 |
| QUALITY/REFERENCE | : POPLAR |
| REPUTED FIBRE CONTENT | : NOT GIVEN |
| FABRIC DESCRIPTION | : WOVEN |
| COLOUR/DESIGN | : PETAL |
| STYLE NUMBER | : 269702 |
| ORDER NUMBER | : 64904 |
| PERFORMANCE STANDARD | : GENERAL |



REQUEST: Hydrostatic head



S. WISEMAN
LABORATORY DIRECTOR

L. SHERIDAN
LABORATORY MANAGER

This report may not be reproduced except in full without the written approval of HSTTS. In all circumstances results of tests are implied as referring only to the sample supplied and should not be construed or interpreted on any other basis. The comments given in the report are for guidance only and are not a part of the results. Where specified in a test method, preconditioning in accordance with ISO 139 is not carried out as samples are exposed to the conditioning atmosphere specified within ISO 139 for a minimum of 16 hours prior to test.



118 Lupton Avenue Leeds LS9 6ED
Tel:0044 (0) 113 248 8830 Fax:0044 (0) 113 248 0239 EMail: hstts@hstts.co.uk
Registered No. 2899980 VAT No. 613 4310 86

Report 322531

PHYSICAL

BS EN 20811:1992 (1996) Hydrostatic Head

| | |
|--------------------------------|--------------------|
| Sample area | 100cm ² |
| Test atmosphere | 20°C 65% R.H |
| Water temperature | 20°C |
| Rate of rise of water pressure | 60cm/1min |

| | |
|--------|--------------|
| Test 1 | >400 cms/H2O |
| Test 2 | >400 cms/H2O |
| Test 3 | >400 cms/H2O |
| Test 4 | >400 cms/H2O |
| Test 5 | >400 cms/H2O |

| | |
|------|--------------|
| Mean | >400 cms/H2O |
|------|--------------|